



PROCESSES:

1. CHIP OUT CONCRETE 1/2" - 1" DEPTH AND CURTAIL 3" - 4" BACK
2. PRIME WITH DEK-641 PENETRATING PRIMER
3. FILL WITH RES-TEK RT-05 LM POLYMER CONCRETE TO WITHIN 150 MILS (OR TOTAL THICKNESS OF FINISHED SYSTEM)
4. RE-PRIME AREAS OF RT-05 LM POLYMER CONCRETE WITH DEK-641 PENETRATING PRIMER
5. FINISH WITH RES-TEK DEK-GUARD VEHICULAR DECK COATING SYSTEM, FLUSH TO TERMINATION